



LABORATORIO PER LA CERTIFICAZIONE E RICERCA
SUI SISTEMI ELASTOMERICI

con il patrocinio del C.N.R.



To

BER-PA S.r.l.

Via Faletti, 16

25031 CAPRIOLO (BS)

Date, May 24th, 2013
TR n° 243_{bis}/2013
Ref. Your Confirmation dated 08.04.2013

Received 16.04.2013 Start tests 18.04.2013 End tests 03.05.2013 Page 1 of 1

T E S T R E P O R T

Subject: DETERMINATION OF THE GROSS CALORIFIC VALUE OF TWO SAMPLES OF FLUORINATED RUBBER COMPOUNDS SUPPLIED AS VULCANIZED SHEETS 2 mm thick

<u>Rubber Compounds</u>	<u>VB75AT52</u>	<u>VB80AT52</u>	<u>Test Methods</u>
-------------------------	-----------------	-----------------	---------------------

<u>Gross Calorific Value</u>	kJ/g	15,089	16,559	ASTM D 5865-12
------------------------------	------	--------	--------	----------------

<u>Gross Calorific Value</u>	J/g	15089	16559	ASTM D 5865-12
------------------------------	-----	-------	-------	----------------

NOTE: Equipment used for the test "Automatic Calorimeter Isooperibolic 6300 CALORIMETER - Parr Instruments Company".

The sampling has been carried out by the Customer.
The contained results refer only to the tested sample.
This report cannot be partially reproduced without the laboratory approval.

F. Negroni
F. Negroni, **Director**